

SANIFLEX PTY LTD

PRODUCT SHEET

LATEX EXAMINATION GLOVES

POWDER FREE - NATURAL

100 PACK

PRODUCT IMAGE	DESCRIPTION																														
	LATEX EXAMINATION GLOVES POWDER FREE - NATURAL 100 PACK ITEM NO.: STL100PF-XS / STL100PF-S / STL100PF-M / STL100PF-L / STL100PF-XL BARCODES BY SIZES: XS - 9356658002615, S - 9356658002622, M - 9356658002639, L - 9356658002646, XL - 9356658002653 UNITS PER BOX: 100 BOX DIMENSIONS: 24 x 12.2 x 6.5cm BOXES PER CARTON: 10 UNITS PER CARTON: 1,000 CARTON DIMENSIONS: 34 x 24.9 x 25cm CARTON WEIGHT: AVE. 6kg FEATURES: MATERIAL: Natural Rubber Latex COLOUR: Natural Single Use, Powder Free, Non Sterilized, Ambidextrous Beaded Cuff, Easy to handle  <table><tr><th>Complies with</th><th>ASTM D3578</th><th>EN 455</th><th>AS/NZS 4011</th><th>SANIFLEX STL100PF</th></tr><tr><td>Length</td><td>XS-S : Min 220mm, M-XL : Min 230mm</td><td>Median ≥240mm</td><td>≥240mm</td><td>≥240mm</td></tr><tr><td>Average thickness at palm (Single Wall)</td><td>Min 0.05mm</td><td>-</td><td>Min. 0.11mm (Textured area) Min. 0.08mm (Smooth area)</td><td>0.10mm</td></tr><tr><td>Tensile Strength</td><td>Before Aging : Min. 18 Mpa After Aging : Min. 14 Mpa</td><td>-</td><td>-</td><td>Before Aging : 27 Mpa After Aging : 15 Mpa</td></tr><tr><td>Force at Break</td><td>-</td><td>Before Aging: Median ≥ 6.0N After Aging: Median ≥ 6.0N</td><td>Before Aging: Min. 7.0N After Aging: Min. 6.0N</td><td>Before Aging: 7.5N After Aging: 7.0N</td></tr><tr><td>Elongation</td><td>Before Aging : Min. 650% After Aging : Min. 500%</td><td>-</td><td>Before Aging: Min. 650% After Aging: Min. 500%</td><td>Before Aging: 790% After Aging: 840%</td></tr></table> STANDARDS: Meets AS/NZS 4011, ASTM D3578, EN455, TGA USAGE:  MEDICAL DENTISTRY FOOD HANDLING LABORATORY JANITORIAL	Complies with	ASTM D3578	EN 455	AS/NZS 4011	SANIFLEX STL100PF	Length	XS-S : Min 220mm, M-XL : Min 230mm	Median ≥240mm	≥240mm	≥240mm	Average thickness at palm (Single Wall)	Min 0.05mm	-	Min. 0.11mm (Textured area) Min. 0.08mm (Smooth area)	0.10mm	Tensile Strength	Before Aging : Min. 18 Mpa After Aging : Min. 14 Mpa	-	-	Before Aging : 27 Mpa After Aging : 15 Mpa	Force at Break	-	Before Aging: Median ≥ 6.0N After Aging: Median ≥ 6.0N	Before Aging: Min. 7.0N After Aging: Min. 6.0N	Before Aging: 7.5N After Aging: 7.0N	Elongation	Before Aging : Min. 650% After Aging : Min. 500%	-	Before Aging: Min. 650% After Aging: Min. 500%	Before Aging: 790% After Aging: 840%
Complies with	ASTM D3578	EN 455	AS/NZS 4011	SANIFLEX STL100PF																											
Length	XS-S : Min 220mm, M-XL : Min 230mm	Median ≥240mm	≥240mm	≥240mm																											
Average thickness at palm (Single Wall)	Min 0.05mm	-	Min. 0.11mm (Textured area) Min. 0.08mm (Smooth area)	0.10mm																											
Tensile Strength	Before Aging : Min. 18 Mpa After Aging : Min. 14 Mpa	-	-	Before Aging : 27 Mpa After Aging : 15 Mpa																											
Force at Break	-	Before Aging: Median ≥ 6.0N After Aging: Median ≥ 6.0N	Before Aging: Min. 7.0N After Aging: Min. 6.0N	Before Aging: 7.5N After Aging: 7.0N																											
Elongation	Before Aging : Min. 650% After Aging : Min. 500%	-	Before Aging: Min. 650% After Aging: Min. 500%	Before Aging: 790% After Aging: 840%																											